














porcelamik

DATA SHEET
FICHA TECNICA

CODIGO PK
PKPD3030LG13
PKPD3030LG14
PKPD3060LG10
PKPD3060LG11
PKPD3060LG12
PKPD3060LG9

NAME OF SERIES OR ITEM NUMBER	30X60
LAST UPDATE	20161010

TECHNICAL CHARACTERISTICS CARACTERISTICAS TECNICAS		PORCELAMIK VALUES / VALORES	NORMA ISO 13006 REQUISITOS / REQUIREMENTS PAVIMENTOS	TEST METHOD AS PER IOS NORM TEST DE ACUERDO A
	LENGTH AND WIDTH DIMENSIONES (MM)	$\pm (0.00 + 0.05) \%$	$\pm 0.5\%$	UNI EN ISO 10545-2
	STRAIGHTNESS OF SIDE RECTITUD LATERAL (MM)	$\pm (0.0 + 0.3) \%$	$\pm 0.5\%$	UNI EN ISO 10545-2
	RECTANGULAR SQUARENESS ORTOGONALIDAD (MM)	$\pm (0.0 + 0.5) \%$	$\pm 0.6\%$	UNI EN ISO 10545-2
	SURFACE FLATNESS PLANARIDAD (MM)	$\pm (0.0 + 0.5) \%$	$\pm 0.5\%$	UNI EN ISO 10545-2
	THICKNESS ESPESOR (MM)	8.8MM	$\pm 5\%$	UNI EN ISO 10545-2
	WATER ABSORPTION ABSORCION DE AGUA	12.0%		UNI EN ISO 10545-3
	BENDING RESISTANCE RESISTENCIA A LA FLEXION	$\geq 23\text{Mpa}$	$\geq 12\text{Mpa}$	UNI EN ISO 10545-4
	BREAKING STRENGTH FUERZA DE ROTURA	$\geq 819\text{ N}$	$\geq 600\text{N}$	UNI EN ISO 10545-4
	CHEMICAL RESISTANCE RESISTENCIA A PRODUCTOS QUIMICOS	GLA	GB Para Esmaltados UB para Pulidos	UNI EN ISO 10545-14
	STAIN RESISTANCE RESISTENCIA A LA MANCHAS	CLASS 5	$\geq \text{Grado } 3$	UNI EN ISO 10545-14
	ABRASION RESISTANCE (PEI) RESISTENCIA A LA ABRASION SUPERFICIAL (PEI)	CLASS3	Max. 175 mm ³	UNI EN ISO 10545-7
	MOHS HARDNESS DUREZA SUPERFICIAL (ESCALA MOHS)	3	MOHS 1-10	UNI EN ISO 10545-7
	SHADE VARIATION CLASS VARIACION DE TONALIDAD	V3	V1-V4	DIN 51094

PACKING INFORMATION
INFORMACION DE EMPAQUES

SIZE FORMATO	M2/BOX M2/CNT	PCS./BOX PZA./CAJA	BOX/PALLET CAJA/PALETA	M2/PALLET M2/PALETA	KG/BOX KG/CAJA	KG/PALLET KG/PALETA
30X60	1.62	9	60	97.2	25	1500

