














DATA SHEET  
FICHA TECNICA

CODIGO PK
PKSP4040FB93

NAME OF SERIES OR ITEM NUMBER	Navarres
LAST UPDATE	January 2016

TECHNICAL CHARACTERISTICS CARACTERISTICAS TECNICAS		PORCELAMIKA VALUES / VALORES	NORMA ISO 13006 REQUISITOS / REQUIREMENTS PAVIMENTOS	TEST METHOD AS PER IOS NORM TEST DE ACUERDO A
	LENGTH AND WIDTH DIMENSIONES (MM)	$\pm (0.06 + 0.08) \%$	$\pm 0.5\%$	UNI EN ISO 10545-2
	STRAIGHTNESS OF SIDE RECTITUD LATERAL (MM)	$\pm (0.02 + 0.02) \%$	$\pm 0.5\%$	UNI EN ISO 10545-2
	RECTANGULAR SQUARENESS ORTOGONALIDAD (MM)	$\pm (0.07 + 0.07) \%$	$\pm 0.6\%$	UNI EN ISO 10545-2
	SURFACE FLATNESS PLANARIDAD (MM)	$\pm (0.01 + 0.04) \%$	$\pm 0.5\%$	UNI EN ISO 10545-2
	THICKNESS ESPESOR (MM)	7.8 mm	$\pm 5\%$	UNI EN ISO 10545-2
	WATER ABSORPTION ABSORCION DE AGUA	$\leq 1.5 \%$	$E \leq 0.50 \%$	UNI EN ISO 10545-3
	BENDING RESISTANCE RESISTENCIA A LA FLEXION	$\geq 25$ MPA	$\geq 35$ Mpa	UNI EN ISO 10545-4
	BREAKING STRENGTH FUERZA DE ROTURA	$\geq 1000$ N	$\geq 1300$ N	UNI EN ISO 10545-4
	CHEMICAL RESISTANCE RESISTENCIA A PRODUCTOS QUIMICOS	$\geq$ UA	GB Para Esmaltados UB para Pulidos	UNI EN ISO 10545-14
	STAIN RESISTANCE RESISTENCIA A LA MANCHAS	Grado 3	$\geq$ Grado 3	UNI EN ISO 10545-14
	ABRASION RESISTANCE (PEI) RESISTENCIA A LA ABRASION SUPERFICIAL (PEI)	Class 3	Max. 175 mm <sup>3</sup>	UNI EN ISO 10545-7
	MOHS HARDNESS DUREZA SUPERFICIAL (ESCALA MOHS)	7	MOHS 1-10	UNI EN ISO 10545-7
	SHADE VARIATION CLASS VARIACION DE TONALIDAD	V3	V1-V4	DIN 51094

PACKING INFORMATION  
INFORMACION DE EMPAQUES

SIZE FORMATO	M2/BOX M2/CNT	PCS./BOX PZA./CAJA	BOX/PALLET CAJA/PALETA	M2/PALLET M2/PALETA	KG/BOX KG/CAJA	KG/PALLET KG/PALETA
40 x 40 cm	1.28	8	72	92.16	22	1580